

AMENDMENTS

Please amend the claims as follows:

14. (Currently Amended) A method of making a smectite clay slurry of a naturally occurring clay, comprising:
- (a) dispersing one or more naturally occurring smectite clays, one or more phosphonate additives and water to form a clay slurry; ~~and~~
 - (b) shearing the clay slurry; and
 - (c) adjusting the pH of the clay slurry to above about 4.5.
15. (Previously presented) A method according to claim 14, wherein the naturally occurring smectite clay is hectorite.
16. (Previously presented) A method according to claim 14, wherein the phosphonate additive is 1-hydroxyethylene-1,1-diphosphonic acid tetra sodium salt.
17. (Previously presented) A method of making a smectite clay slurry of a naturally occurring clay according to claim 14, wherein the shearing is performed by a Gaulin homogenizer.
- 18-22. (Cancelled)
23. (Currently Amended) A method of making a smectite clay slurry of a naturally occurring clay, comprising:
- (i) dispersing one or more naturally occurring smectite clays and one or more phosphonate additives with water to form a clay slurry, wherein the phosphonate additives are selected from the group consisting of:
 - a) Diphosphonic acids of formula $R^1R^2C(PO(OH)_2)_2$,
 - b) Disphosphonic acids of formula $R^1-CR^2(PO(OH)_2)-R^3-CR^2PO(OH)_2-\underline{R^1R^5}$, ~~and~~
 - c) salts thereof, and
 - d) Phosphonic acid salts of formula $R^1R^4C=C(PO(OH)_2)_2$.

where R¹ is selected from the group consisting of H, a linear or branched alkyl, alkene, hydroxyalkyl, aminoalkyl, hydroxyalkene, aminoalkene with 1 to 22 carbon atoms and an aryl, hydroxyaryl, aminoaryl with 6 to 22 carbon atoms; R² is selected from the group consisting of R¹ and OH; R³ is an alkyl with 0 to 22 carbon atoms; and ~~both R⁴ is and R⁵ are~~ selected from the group R¹; and

(ii) shearing the clay slurry; and -

(iii) adjusting the pH of the clay slurry to above about 4.5.

24. (Cancelled) The method of claim 14, wherein said dispersing is performed in the absence of an organic liquid.
25. (Previously presented) The method of claim 14, further comprising preparing a dry mix of the naturally occurring clay and one or more phosphonate prior to dispersing with water.
26. (Previously presented) The method of claim 23, further comprising preparing a dry mix of the naturally occurring clay and one or more phosphonate prior to dispersing with water.
27. (New) The method of claim 14 wherein at least one of the one or more naturally occurring smectite clays are sodium exchanged clays.
28. (New) The method of claim 14, further comprising adjusting the pH of the clay slurry to above about 5.5.
29. (New) The method of claim 14, further comprising adjusting the pH of the clay slurry to between about 6 to 11.
30. (New) A method of making a smectite clay slurry of a naturally occurring clay, comprising:
 - (a) dispersing one or more sodium exchanged naturally occurring smectite clays, one or more phosphonate additives and water to form a clay slurry;
 - (b) shearing the clay slurry; and
 - (c) adjusting the pH of the clay slurry to above about 4.5.